Snowflake White | 71.100ACTN

This vehicle wrap offers exceptional dimensional stability and long-term durability, making it ideal for vehicle graphics and signage. Suitable for both indoor and outdoor use, it provides easy cutting and weeding, along with excellent conformability. The film can be removed without leaving adhesive residue within 3 years under controlled conditions. The Air Channel Technology (ACT) prevents air bubbles and wrinkles during application.

FACE FILM

Hybrid PVC, gloss white

Thickness (µm)	100	
Opacity	High	
Film colour	RAL 9003 (nearest)	
Tensile strength (N/mm²)	>28	EN ISO 527-3
Elongation at break (%)	>140	EN ISO 527-3

ADHESIVE

Clear solvent-based acrylic, semi-permanent

Thickn	ess (μm)	22	
Adhesi	ion to steel	FINAT	FTM 1
_	20 minutes (180°) N/25mm	15	
	24 hours (180°) N/25mm	18	

RELEASE LINER

Structured lay-flat kraft paper liner, double-sided PE-coated

Weight (gsm)	120
	-

PRODUCT APPLICATION

Application method	Dry	
Dimensional stability (.mm)	<0,5	FINAT FTM 14
Application temparature (°C)	10 to 30	
Service temperature (°C)	-20 to 70	



Groendreef 35 / B-9880 Aalter / T +32 9 216 67 00 / info@fourbases.eu / isee2.com



DURABILITY		
Shelf life (months)	12	
Outdoor durability (years)	8	Vertical exposure, Mid-EU climate

ROLL SIZES

1524mm x 25m 1524mm x 50m

Fourbases BV guarantees the material for twelve months from the date of final invoice. The shelf life of our material depends on storage conditions. The end user should store the material in the original boxes or in equivalent boxes, away from direct sunlight, at a temperature of 21°C and 50% relative humidity. Fourbases BV guarantees that the products are free from defects in workmanship or defects in iSee2 material, provided they are stored properly. At its sole discretion, Fourbases **See2** BV may either: (1) replace all or part of the materials, or (2) issue a credit note for the value of the defective portion. All quoted data values are typical and should not be used as a basis to consider the product defective if measured values differ.



2/2